



Report of product test

製表日期 2024.08.16

品名 item no	嘉鴻牌鋼板擦拭紙(平紋)		檢測結果 result of test	執行標準 Voluntary standards
基本 資訊 Basic information	原料配比 composition (%)		木漿紙 woodpulp 55%	FZ/T64012
			滌綸 polyester 45%	
	實測克重 gsm (g/m ²)		55	
	厚度 thickness(mm)		0.26	
	吸水速率 speed of absorbability(s/5cm)		52	
	吸液量 capacity of liquid-absorbability(%)		461	
	白度 white degree (%)		79.7	(檢測儀器) YG065-II text instrument
物理指標 physical parameters	斷裂強力 breaking strength (N/5cm)	橫 (CD)	45.8	FZ/T64012
		縱 (MD)	160.9	
	斷裂伸長 breaking elongation (%)	橫 (CD)	106.8	
		縱 (MD)	29.8	
	撕裂強度 tearing strength (N/5cm)	橫 (CD)	12.5	
		縱 (MD)	4.3	
檢測日期 date of test	2024.08.15		檢驗 test man	潘文

